

Certificate of Analysis

Dated: 15/04/2014

CLIENT: HPM Legrand 4/44 Lyn Parade Prestons NSW 2170	OUR REF: 1403575 This CofA supersedes CofA No 1403575 dated 10/03/2014
ATTN: Ben Miles	ORDER NO: Not given
SAMPLE DESCRIPTION: Sample 1: Sample 2: PC/ ABS material	DATE RECEIVED: 28/02/14 DATE COMMENCED: 04/03/14
EXAMINATION: JISZ 2801: 2010	Dilution: Neat
Recovery Broth: 0.1% Peptone Water +0.5% Tween80 (PTW)	Recovery volume: 50mL/ sample

Method Description:

Six (6) pieces of untreated and three (3) pieces of treated specimen were transferred aseptically into sterile petri dishes separately facing up. Top surface of each test piece was inoculated with 1.5 mL of challenge organism and covered with sterile film to spread the inoculum. Three inoculated pieces each of treated and untreated specimen were incubated at 37°C.

Counts were performed on 3 untreated materials soon after inoculation. Each inoculated test material was transferred into a stomacher bag and 50mL of PTW was added into it. Stomacher bag was sealed using a heat sealer and shaken for 1 minute. Appropriate dilutions (-2 to -3 for untreated specimen soon after inoculation and -1 to -6 for specimen after incubation) were performed using phosphate buffer physiological saline. The plates were poured with TSA and incubated at 37°C for 24 ±1 hour. Counts were performed at the end of incubation period for both treated and untreated materials.

Challenge Organisms: *Staphylococcus aureus* ATCC 6538

Escherichia coli ATCC 8739

RESULTS:

Table 1: Antibacterial Activity result on PC/ ABS material against *S. aureus*.

<i>Challenge organism:</i>		<i>S.aureus</i>		Sample:		PC/ ABS	
Specimen:	Test condition	CFU / mL				Condition of a valid test	
	Temp. / incubation period	Replicate 1	Replicate 2	Replicate 3	Mean		
Control	immediately after inoculation	2.8 x10 ⁵	2.8 x10 ⁵	2.9 x10 ⁵	2.8 x10 ⁵	≤0.2	
Log value		5.45	5.45	5.46	5.45	0.00	
Control	after 24hrs ± 1hr incubation @ 37°C	2.6 x10 ⁷	5.3 x10 ⁶	5.5 x10 ⁶	1.2 x 10 ⁷	-	
Log value		7.41	6.72	6.74	7.08	-	
Treated	after 24hrs ± 1hr incubation @ 37°C	1.5 x10 ³	9.0 x10 ²	7.2 x10 ⁴	2.5 x10 ⁴	Log reduction	
Log value		3.18	2.95	4.86	4.39	2.70	

Table 2: Antibacterial Activity result on PC/ ABS material against *E. coli*.

<i>Challenge organism:</i>		<i>E.coli</i>		Sample:		PC/ ABS	
Specimen:	Test condition	CFU / mL				Condition of a valid test	
	Temp. / incubation period	Replicate 1	Replicate 2	Replicate 3	Mean		
Control	immediately after inoculation	4.3 x10 ⁵	4.3 x10 ⁵	4.2 x10 ⁵	4.3 x10 ⁵	≤0.2	
Log value		5.63	5.63	5.62	5.63	0.00	
Control	after 24hrs ± 1hr incubation @ 37°C	2.2 x10 ⁸	1.8 x10 ⁸	1.6 x 10 ⁸	1.8 x 10 ⁸	-	
Log value		8.34	8.20	8.20	8.25	-	
Treated	after 24hrs ± 1hr incubation @ 37°C	3.7x10 ⁵	1.1 x10 ⁶	6.4 x10 ⁴	5.1 x10 ⁵	Log reduction	
Log value		5.57	6.04	4.81	5.70	2.55	

FINAL RESULTS:

The sample "**PC/ ABS material**" has passed the acceptance criteria set forth in JIS Z 2801:2010, by showing significant antibacterial activity of 2.70 Log reductions against *Staphylococcus aureus* and 2.55 log reductions against *Escherichia coli*, when tested under the conditions described above

Medium Used:

Tryptic Soy Agar -260814

0.1% PTW -110514

Peptone Water: 210514

Nutrient Broth 190514

Signed:

Imtiaz Ahmed

Sterile Products Testing Manager

